

1.4.1A.1 Hardwood Laminates: Product Data Sheet

	FormWood paper back veneer	NBL	DuraBack	FormWood 2 Ply	PSA backed 10 Mil veneer	Hot Melt Backed 10 Mil Veneer (2'x8')	Crotch Cut Materials (on Two-Ply)
Thickness	.020"	.040"	.038-.048"	.040"	.025"	.033"	.074"
Recommended Glue	SC, UF	SC, UF	WC, SC, UF	SC, UF	SA	SA	SC, UF
Size Availability	1,2,3,4,5,6,7,8,9	1,2,3,4,5,6	1,2,4,5,6,7	1,2,3,6,8	1,2,6	6	1
Bending Radius	T	M	M	M	T	M	F
Pounds/Sheet (4'x8' unless noted)	3.1 (for 10 Mil)	3.94	6.9	3.94	4.41	1.8	4.5

Recommended Glue Key

WC = water-based contact (flexible glue line)

SC = solvent-based contact (flexible glue line)

UF = urea formaldehyde cured in a press (rigid glue line)

SA = Self-adhering

Size Key

1 = 2'x8', 4'x8'

2 = 4'x8', 4'x10'

3 = 8'x4', 10'x4'

4 = 5'x8', 5'x10'

5 = 4'x12'

6 = 2'x8', 2'x10'

7 = 5'x12'

8 = 8'x5', 10'x5'

9 = 12'x4'

Bending Radius Key

T = Tight

M = Moderate

F = Flat Applications